

Material : EPDM

Product Code : SEP 140 / SEP 180

ITEM	UNIT	SEP 140	SEP 180
Apparent Density	gr / cm ³	0.14±0.03	0.18±0.03
Tensile Strength	kg / cm ²	7.6	8
Elongation at Break	%	200	168
Hardness (C-Type)	HS	15±3	20±3
Heat Shrinkage (70°C x 4 hr)	%	4	4
Compression Strength (25% Deflection)	kg/100cm ³	30±10	35±10
Compression Set (50% Deflection, 20°C x 22hr)	%	25	25
Water Absorption	gr / cm ³	0.005	0.005

Test Method :ASTM-D1056 & KS M 3014 & KS M 6550